

# Materials R&D Requirements for Fossil-Fuelled Steam Plant

Steve Osgerby

Energy materials – Meeting the Challenge

09/10/2008

**ALSTOM**

# Why is Steam Plant a key issue?



74% of the UK's electricity demand is met by fossil-fuelled plant

- 38% coal- or oil-fired
- 36% gas-fired
  - Split between open cycle (gas turbine only) and combined cycle (gas turbine + steam turbine)

⇒ >50% of UK electricity dependent on steam plant

- Boilers
- Steam turbines


# Key Drivers

---



- Economic
  - Improved efficiency
  - Reliability
  - Manufacturing Costs
  
- Environmental
  - Improved efficiency = lower emissions
  - Carbon capture

# Cost of reduction in CO<sub>2</sub>



Ref: Stamatelopolous "Clean Combustion Technologies 2- Pulverised Fuel Technology, Brussels 2005

- Higher Inlet Temperatures
  - Boilers
  - Steam Turbines

⇒ Materials with Higher Temperature Capability
  
- More efficient LP turbines
  - Optimise aerodynamic design
  - Increase exhaust area

⇒ Higher Strength Materials with SCC Resistance

# High Level Requirements: Implementation

## – 5 years

---



- Incremental improvements in existing materials systems
- Production/characterisation of prototype components using identified materials and processes
- Repair and improvement solutions for existing plant and materials
- Advanced manufacturing development for existing materials/processes for cost reduction/increased performance and integrity

# High Level Requirements: Implementation

## – 10 years

---



- Development of new materials systems (substrate + coatings) based on existing knowledge including behaviour in realistic environments
- Development and application of process modelling to new materials to speed up introduction and help define new system solutions
- Adopting a total system approach to critical part design and life prediction with multi-material components with joints and coatings

# High Level Requirements: Implementation

## – 20 years

---



- Identification of disruptive novel material systems and initial characterisation to identify most promising approaches
- Development of novel advanced technologies that will enable high overall efficiencies that will significantly reduce emissions



# High Level Requirements:Generic Research

---




- Surface Protection Technologies
- Improved understanding and predictive modelling of degradation mechanisms
- Non-invasive inspection techniques for in situ assessment of material condition
- Existing plant refurbishment
- Similar and dissimilar materials joints

# Boilers: Furnace Walls

## State-of-the-Art

- Low alloy steels T23 and T24
- Designed for use without PWHT



## Future Requirements

- Higher temperature capability
- Fireside Corrosion Resistance

## Possible Solutions

- Ni-base alloys (IN617, IN740)
- New steels with surface protection

## State-of-the-Art

- High Cr austenitic steels (NF709, HR3C, Sanicro 25)

## Future Requirements

- Higher temperature capability
- Fireside Corrosion Resistance

## Possible Solutions

- Ni-base alloys (IN740)
- Materials with properties intermediate between austenitic steels and Ni-base alloys (AC66)

## State-of-the-Art

- 9-12%Cr Martensitic Steels (P92, E911)



*Nimonic 263 Extrusion*

## Future Requirements

- Higher temperature capability
- Steam Oxidation Resistance
- Eliminate Type IV Cracking

## Possible Solutions

- High boron steels
- Coating of internal surfaces
- Ni-base alloys

## State-of-the-Art

- 9-12%Cr Martensitic Steels (X13CrMoCoVNbNB 9 2 1)



## Future Requirements

- Higher temperature capability
- Inspectability

## Possible Solutions


- Ni-base alloys
- Cooling technology / thermal barrier coatings

# Steam Turbines: Casings and Valve Chests



## State-of-the-Art

- 9-12%Cr Martensitic Steels  
(G-X13CrMoCoVNbNB 9 2 1)



## Future Requirements

- Higher temperature capability
- Castability / Weldability

## Possible Solutions

- Ni-base alloys

## State-of-the-Art

- 9-12%Cr Martensitic Steels  
(X20CrMoV 12 1)
- Austenitic Steels



## Future Requirements


- Higher temperature capability
- Solid Particle Erosion Resistance

## Possible Solutions

- Ni-base alloys
- Erosion Resistant Coatings

## State-of-the-Art

- 9-12%Cr Martensitic Steels  
(X20CrMoV 12 1)
- 'Stellite' hardfacing



## Future Requirements

- Higher temperature capability
- Erosion/Corrosion Resistance

## Possible Solutions

- Ni-base alloys
- Abrasion Resistant Coatings



## State-of-the-Art

- NiCrMoV steels
- Surface treatment



## Future Requirements

- Higher strength
- SCC resistance

## Possible Solutions

- More highly alloyed steels
- Improved surface treatment

## State-of-the-Art

- PH-stainless steels
- Surface treatment



## Future Requirements

- Higher strength
- SCC resistance

## Possible Solutions

- High strength steels with SCC resistance
- High strength steels with protective coatings

# Is success achievable?



Issue	Expertise required	Available in UK Industry	Available in UK academia / research establishments
Materials with increased strength at high temperature	Alloy development	Yes	
	Materials modelling		Yes
	Long term test capability	Yes	??
Development of coatings	Coating processing technology	Yes	Yes
	Compositional development of coatings		Yes
	Long/short term test capability	Yes	Yes

© ALSTOM 2008. All rights reserved. Information contained in this document is provided without liability for information purposes only and is subject to change without notice. No representation or warranty is given or to be implied as to the completeness of information or fitness for any particular purpose. Reproduction, use or disclosure to third parties, without express written authority, is strictly prohibited.

# Is success achievable?



Issue	Expertise required	Available in UK Industry	Available in UK academia / research establishments
Surface Processing	Processing to develop residual stress profile	Yes	
	Understanding of residual stress development	Yes	Yes
	Long/short term test capability	Yes	Yes
High strength SCC resistant alloys	Alloy development	Yes?	
	Materials modelling		
	Long term test capability	Yes	Yes

# Threats to success

---



- Materials systems approaching physical temperature limits for applicability
- Long timeframe for materials development cycle – does not fit with 3-4 year funding cycles
- Growing shortage of graduates with necessary skills

# High Level Actions Required



- Development of integrated strategy for Energy Materials Development, buy-in from
  - Funding agencies
  - Industry
  - Academia
- Commitment to long-term funding to cover entire materials development cycle
- Active encouragement for pre-competitive collaboration, both national and international
- Attract and retain high quality students/graduates within the Energy Materials field

[www.alstom.com](http://www.alstom.com)

**ALSTOM**